US005147396A

United States Patent [19]

Kageyama et al.

[11] **Patent Number: 5,147,396**

[45] **Date of Patent: Sep. 15, 1992**

[54] **INTRAOCULAR LENS**

[75] Inventors: **Mayumi Kageyama**, Akishima; **Takeyuki Sawamoto**, Tokyo; **Niro Tarumi**, Akishima; **Hiroshi Sakai**, Kodaira, all of Japan

[73] Assignee: **Hoya Corporation**, Tokyo, Japan

[21] Appl. No.: **327,701**

[22] Filed: **Mar. 23, 1989**

[30] **Foreign Application Priority Data**

Mar. 28, 1988 [JP] Japan 63-73559

[51] **Int. Cl.**[5] **A61F 2/16**

[52] **U.S. Cl.** ..... **623/6**; 351/160 H; 523/113

[58] **Field of Search** ..... 623/6; 351/160 H; 523/113; 522/26, 99, 50; 528/31, 32

[56] **References Cited**

U.S. PATENT DOCUMENTS

4,143,949	3/1979	Chen	351/160 H
4,153,641	5/1979	Deichert	351/160 H X
4,537,943	8/1985	Talcott	528/31 X
4,582,884	4/1986	Ratkowski	528/32 X
4,740,533	4/1988	Su et al.	528/32 X
4,795,461	1/1989	Lindquist et al.	623/6
4,803,254	2/1989	Dunks et al.	623/6 X
4,872,877	10/1988	Tiffany	623/6

Primary Examiner—Alan W. Cannon
Attorney, Agent, or Firm—Nixon & Vanderhye

[57] **ABSTRACT**

An intraocular lens whose optic or optic and haptic are composed of a substantially soft polymer obtained by curing a composition comprising:

(a) a dimethylsiloxane-phenylsiloxane copolymer having a vinyl group at each of the both terminals of the molecular chain,

(b) a diorganopolysiloxane having at least three hydrosilyl groups in the molecule, and

(c) an U.V. absorber.

The intraocular lens obtained above has good intraocular stability, excellent biocompatibility, high optical properties and an U.V. absorbability closer to that of the human lens.

By further incorporting a filler as the component (d), the intraocular lens has improved mechanical properties and higher intraocular stability.

14 Claims, No Drawings